



www.silkpaint.com
art@silkpaint.com
1 800-563-0074

Carving Paper and Fiber Etch®

Apply Fiber Etch® from bottle, with brush, through a silkscreen, or over a freezer paper stencil.*

Place in oven to both dry and activate at 200° for approximately 10 minutes. Treated areas will be light to medium brown in color.

*As noted in the Velvet Paper™ "Stenciled Shapes" instructions.

Carving Paper™
With freezer paper stencil



Using a piece of glass or a flat sheet pan under Carving Paper™ for support, rinse under trickling water, tapping areas very gently with a soft toothbrush to remove paper bits. Blot with a towel. Allow to air dry flat.

If color is desired, immerse Carving Paper into a color bath of watercolor. Allow to dry.